

TEXTURE FINE SAND FINISH

RESOURCE CODE 210030
FEBRUARY 2022
PAGE 1 OF 3



Description & Uses

Baxta Texture Fine Sand Finish is a high performance pre-mixed polymer render allowing quick and easy thin section rendering. Baxta Texture Fine Sand Finish comes ready for use and is applied by trowel up to 4mm in a single application. Multiple coats of Baxta Texture Fine Sand Finish may be applied for rectification of severe defects. Baxta Texture Fine Sand Finish can be finished with a styropor float, plastic trowel or sponged to give a rendered finish. Baxta Texture Fine Sand Finish is used as the rendering system on fibre cement sheets prior to the application of low profiled texture systems. Baxta Texture Fine Sand Finish can also be applied over previously painted surfaces.

Features & Benefits

- | | |
|--|--|
| <ul style="list-style-type: none"> • Sophisticated grainy texture • Pigmented with crushed and graded marble | <ul style="list-style-type: none"> • Fast finishing properties allow for floating almost immediately • Interior and exterior use |
|--|--|

Colours & Gloss

White. Do not tint Baxta Texture Fine Sand Finish.

Matt.

Properties & Performance Guide

Dry & Recoat Times	<p>Surface Dry - 4 hours Recoat - 24 hours Fully Cured - 7 days</p> <p>Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.</p>
Coverage per Coat	1.5Kg/M ² (per 1mm film build).
Wet Film Thickness Dry Film Thickness	<p>2000 microns (approx). 1300 microns (approx).</p>
Clean Up	<p>Clean up with cold water away from drains.</p> <p>Protect Our Environment: Unwanted Baxta Texture Fine Sand Finish should be kept in a sealed container, and then disposed of via special waste collection services. Empty Baxta Texture Fine Sand Finish containers should be left open in a well ventilated area to dry out. Disposal of empty paint containers may differ between local authorities. Check with your local council first.</p>

TEXTURE FINE SAND FINISH

RESOURCE CODE 210030
FEBRUARY 2022
PAGE 2 OF 3

Recommended Substrate Conditions & Preparation

Work Area: Care should be taken to keep product off windows and adjacent surfaces that are not to be coated, as product can be very difficult to remove once allowed to dry. Use drop sheets to cover surroundings surfaces. Ensure air movement and ventilation while painting. Keep doors and windows open.

Substrate Condition: Baxta Texture Fine Sand Finish may be applied to a wide variety of suitably prepared surfaces including fibre cement sheeting, polystyrene sheets, sills and mouldings, and Autoclaved Aerated Concrete (AAC). The substrate must not be subjected to continual wetting or hydrostatic pressure. Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, application must be carried out according to Baxta's recommendation.

Surface Prep: Ensure the surface is clean and dry. All substrates must be free of dirt, grease, oil, mould, release agents, bondbreakers or any other contaminants that may interfere with adhesion. Fresh cementitious substrates should be left for a minimum 28 days before coating. There must be less than 15% moisture content in the surface at the time of coating to ensure optimum coating performance. The substrate must not be subjected to continual wetting or hydrostatic pressure. All substrates must be installed as per manufacturers' specifications prior to application.

Application Guide

Stir contents thoroughly with a power stirrer before use.

For application to fibre cement sheets:

Apply one (1) coat of Baxta Texture Fine Sand Finish by trowel @ 1.5 Kg/M² per 1mm thickness required. Allow to dry. Freshly applied material must be protected from frosts and rain for a minimum of forty-eight (48) hours. Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C or when humidity is very high. The temperature must not fall below 10°C during the drying process. In exterior application avoid painting when dew or rain is likely.

Additional Data

Available in 15 litre (22.8 Kg) containers.

NOTE: Baxta Texture Fine Sand Finish is a preparation coat and must be used as part of an approved system.

Avoid exposure to steam and condensation for 48 hours after application of final coat.

Leave 7 days after application of final coat before washing. Wash using a sponge or soft cloth with warm water and mild detergent. Avoid harsh scrubbing and strong household cleaners.

Not suitable for horizontal roofs, ponds or walk-on surfaces.

Containers must be secured and stored upright during transit.

Containers must not be exposed to excessive heat or cold.

Store in a secure, cool and well ventilated place. Keep container tightly closed.

Do not use for any other purpose other than as specified.

Manufacturers Comment

This product has been designed as part of a totally integrated coating system. Failing to follow application instructions or use with other manufacturer's product, could result in detrimental effects on product performance for which Baxta Industries Pty Ltd cannot be held responsible.

TEXTURE FINE SAND FINISH

RESOURCE CODE 210030

FEBRUARY 2022

PAGE 3 OF 3

Safety Data	
First Aid Instructions	<p>For advice, contact the Poisons Information Centre on 131 126 (Australia) or a doctor.</p> <p>If in eyes, wash out immediately with water. Remove contact lenses if present and easy to do so, continue rinsing.</p> <p>If skin contact occurs remove contaminated clothing and flush contaminated skin with water.</p> <p>If inhaled remove from contaminated area to fresh air.</p> <p>If swallowed, do not induce vomiting. Give a glass of water to drink.</p>
Safety Directions	<p>Keep out of reach of children.</p> <p>Avoid contact with skin and eyes.</p> <p>Ensure adequate ventilation during use.</p> <p>Avoid prolonged breathing of vapour.</p> <p>Wash hands thoroughly after use.</p>
Further Information	<p>Safety Data Sheet and Product Information can be found at www.baxta.com.au or by calling 1300 85 55 40.</p>